

Indice Generale - *General Index*

**"TERMOPLASTICO ESENTE DA ALOGENI" "HALOGENS FREE THERMOPLASTIC"**

**GUAINA / ISOLAMENTO SHEATH / INSULATION**

Vibiplast <i>Product Name</i>	Specific Gravity <i>kg/dm<sup>3</sup></i>	Hardness <i>Shore D</i>	Oxygen Index <i>% O<sub>2</sub></i>	Ultimate Tensile Strength <i>N/mm2</i>	Elongation at Break <i>%</i>	Description	The product can be used in accordance with the following rules:						Notes
							EN 50363-0	EN 50363-7 / 8	BS 7655	VDE 0207 Part 23 / 24	IEC 92-359	IEC 60502	
HL 100 / E / TB	1.49	49	30	11	170	HFFR, for sheath and insulation. Operating temperature 90°C.	M1	TI7	LTS1	HM2 HM4 HJ2	SHF1		
HL 101 / 5	1.38	Shore A 90	34	13	230	HFFR for sheath and insulation. Elastic product with good flexibility, ideal for small thicknesses. Operating temperature 90°C	M1	TI7 TM7	LTS1	HM2 HM4	SHF1		
HL 101 / 6	1,41	Shore A 92	30	13	230	HFFR for sheath and insulation. Elastic product with good flexibility, ideal for small thicknesses. Operating temperature 90°C	M1 M9	TI7	LTS1	HM2 HM4	SHF1		
HL 104 / LT	1,52	50	34	11	170	HFFR for sheath and insulation. Operating temperature 90°C	M1	TI6 TI7 TM7	LTS1 LTS3	HM2 HM4	SHF1	ST8	
HL 104 / TB	1,50	50	34	9,5	160	HFFR for sheath. Operating temperature 90°C	M1		LTS1	HM2 HM4	SHF1		
HL 106 / TB	1,40	48	27	11	> 200	HFFR for sheath and insulation Ideal for thin thicknesses. Operating temperature 90°C	M1	TI6 TI7	LTS1	HM2 HM4	SHF1		
HL 107 / TB	1,49	Shore A 93	34	11	195	HFFR for sheath and insulation. Elastic product with good flexibility. Operating temperature 90°C	M1	TI7 TM7	LTS1	HM2 HM4	SHF1		
HL 108 - 105 / TB	1,50	55	37	13	170	HFFR for sheath and insulation ideal for HIGH TEMPERATURE. HFFR for high temperature (105 C°). Exceeds aging at 135°C x 336 h. Operating temperature 105°C	M1	TI6 TI7	LTS1	HM2 HM4 HJ2	SHF1	ST8	
HL 108 / ARTIC / UV - UL	1,52	46	37	12	185	HFFR for sheath and insulation ideal for COLD climate conditions. HFFR designed to withstand low temperatures, - 60 ° C fixed installation. UV Resistant Method UL 2556. Operating temperature 70°C	M1			HM2 HJ2		ST8	
HL 108 / IRC / TB	1,54	51	34	11	155	HFFR for sheath. Operating temperature 90°C	M1		LTS1	HM2 HM4	SHF1		
HL 108 / Plus	1,55	55	40	12,5	155	HFFR for sheath. CHAR-FORMING with high performance flame retardant, no dripping. Ideal for CPR applications. Operating temperature 90°C	M1 M16 M20			HM2 HM4	SHF1	CPR	
HL 108 / TB	1,53	53	38	12	160	HFFR for sheath and insulation. Operating temperature 90°C	M1	TI6 TM7	LTS1	HM2 HM4	SHF1	ST8	
HL 108 / VTM / TB	1,54	51	31	12	170	HFFR for sheath. Operating temperature 90°C	M1		LTS1	HM2 HM4	SHF1		

Indice Generale - General Index

"TERMOPLASTICO ESENTE DA ALOGENI" "HALOGENS FREE THERMOPLASTIC"

GUAINA / ISOLAMENTO SHEATH / INSULATION

Vibiplast	Specific Gravity	Hardness	Oxygen Index	Ultimate Tensile Strength	Elongation at Break	Description	The product can be used in accordance with the following rules:						Notes
							EN 50363-0	EN 50363-7 / 8	BS 7655	VDE 0207 Part 23 / 24	IEC 92-359	IEC 60502	
Product Name	kg/dm <sup>3</sup>	Shore D	% O <sub>2</sub>	N/mm <sup>2</sup>	%								
HL 116 / Plus	1,47	49	33	11	180	HFFR for sheath and insulation ideal for insulation CPR. Good processability. Operating temperature 70°C	M1	TI6 TI7		HM2 HJ2	SHF1	ST8	CPR
HL 116 / TB	1,47	49	30	11	180	HFFR for sheath and insulation ideal for insulation. Good processability. Operating temperature 70°C	M1	TI6 TI7		HM2 HJ2	SHF1	ST8	
HL 208 / Plus	1,55	52	36	11	145	HFFR for sheath and insulation, <u>no dripping</u> . This product contain a special mix of filler than during the combustion, forms a compact solid coating. This coating protects the internal cables and does not drip. Ideal for CPR application. Operating temperature 90°C	M1 M16 M20	TI7 TM7	LTS1 LTS3	HM2 HJ2	SHF1		CPR
HL 208	1,53	51	35	11	160	HFFR for sheath and insulation, <u>no dripping</u> . This product contain a special mix of filler than during the combustion, forms a compact solid coating. This coating protects the internal cables and does not drip. Ideal for CPR application. Operating temperature 90°C	M1 M16 M20	TI7		HM2 HM4 HJ2	SHF1		CPR
HL 210 / TB	1,54	51	30	10,5	140	HFFR for sheath, <u>no dripping</u> . This product contain a special mix of filler than during the combustion, forms a compact solid coating. This coating protects the internal cables and does not drip. Operating temperature 90°C	M1		LTS1 LTS3	HM2 HM4	SHF1		
HL 300 / E / TB	1,50	49	32	10	165	HFFR for sheath and insulation. Good processability. Operating temperature 90°C		TI6 TI7	LTS1	HM2 HM4 HJ2	SHF1		
HL 301 / TB	1,55	51	34	11	155	HFFR for sheath. Good processability. Operating temperature 90°C	M1			HM2 HM4	SHF1		
HL 308 / TB	1,56	51	39	12	160	HFFR for sheath. Good processability. Operating temperature 90°C				HM2 HM4	SHF1		
HL 310 / FT	1,47	50	38	12	175	HFFR for sheath and insulation. Good processability. Operating temperature 90°C	M1	TI6 TM7	LTS1 LTS2	HM2 HM4			
HL 310 / R / TB	1,51	51	37	12	180	HFFR for sheath and insulation. Good processability. Operating temperature 90°C	M1	TI6 TI7	LTS2	HM2 HM4 HJ2	SHF1		

Indice Generale - *General Index*

**"TERMOPLASTICO ESENTE DA ALOGENI" "HALOGENS FREE THERMOPLASTIC"**

**GUAINA / ISOLAMENTO SHEATH / INSULATION**

Vibiplast <i>Product Name</i>	Specific Gravity <i>kg/dm<sup>3</sup></i>	Hardness <i>Shore D</i>	Oxygen Index <i>% O<sub>2</sub></i>	Ultimate Tensile Strength <i>N/mm2</i>	Elongation at Break <i>%</i>	Description	The product can be used in accordance with the following rules:						Notes
							EN 50363-0	EN 50363-7 / 8	BS 7655	VDE 0207 Part 23 / 24	IEC 92-359	IEC 60502	
HL 310 / TB	1,50	51	39	12	170	HFFR for sheath and insulation. Good processability. Operating temperature 90°C	M1	TI6 TI7	LTS1 LTS2	HM2 HM4 HJ2	SHF1	ST8	
HL 312 / TB	1,51	53	35	12	170	HFFR for sheath and insulation. Good processability. Operating temperature 90°C	M1	TI6 TI7	LTS1 LTS2	HM2 HM4		ST8	
HL 316 / TB	1,52	51	41	11	160	HFFR for sheath and insulation. Good processability. Operating temperature 90°C	M1	TI6 TI7		HM2 HM4 HJ2	SHF1		
HL 400 / UV - UL / EM	1,42	51	30	12	190	HFFR for sheath ideal for HOT climate conditions. HFFR. Excellent resistance to tearing and hot pressure performance. UV - Resistant, Metod UL 2556. Operating temperature 90°C	M1		LTS1	HM2 HM4	SHF1	ST8	
HL 505 / Plus	1,56	53	40 ± 1	13	150	HFFR for sheath. CHAR-FORMING and ANTI-DRIPPING with a very high performance flame retardant, ideal for CPR applications. Operating temperature 90°C	M1 M16			HM2 HM4	SHF1		CPR
HL 505	1,56	55	40	13	150	HFFR for sheath. CHAR-FORMING and ANTI-DRIPPING with a very high performance flame retardant, ideal for CPR applications. Operating temperature 90°C	M1 M16 M20			HM2 HM4	SHF1		CPR
HL 600 / 2	1,56	55	42	13	110	HFFR for sheath, CHAR-FORMING and ANTI-DRIPPING. Operating temperature 90°C. extreme fire resistance.			LTS3				
HL 703 / TB	1,57	48	36	11,5	180	HFFR for sheath, Elastic product with excellent flexibility. Ideal for extrusion sheath and insulation. Operating temperature 70°C	M1 M16 M20	TI6 TI7		HM2 HJ2	SHF1	ST8	VDE 0250 part 251 HM5
HL MORBIDO	1,50	40	30	7,5	200	HFFR for sheath. Soft and Flexible. Operating temperature 70°C		TM7		HM2			
HL STAMP / A	1,36	40	32	7	300	HFFR for Molding. The product can be used to molding electric plugs / technical articles. Operating temperature 90°C							Molding
HL STAMP	1,42	40	25	9	350	Halogen Free for Molding. The product can be used to molding electric plugs / technical articles. Operating temperature 90°C							Molding

**UV** : All the products listed are available **UV - UL** comply at the Metod UL 2556.

**ART** : All the products listed are available in **Anti-mouse Anti-termite** version.