

Indice Generale - *General Index*

"RIEMPITIVO ESENTE DA ALOGENI" "HALOGENS FREE FILLER"

RIEMPITIVO FILLER / BEDDING

Vibiplast	Specific Gravity	Hardness	Oxygen Index	Mooney Viscosity	Product base	Drummability of the product		Suitable for Tandem	Notes
<i>Product Name</i>	<i>kg/dm<sup>3</sup></i>	<i>Shore A</i>	<i>% O<sub>2</sub></i>	<i>ML (1+4) 100°C</i>		Drummable	Not Drummable		
Filler 1 / GRM	1.65	50	---	45 ± 5	Rubber	✓		✓	
Filler 2 / GRM	1.60	50	26.5	45 ± 5	Rubber	✓		✓	
Filler 10 / GRM	1.68	65	> 30	90 ± 5	Rubber	✓		✓	
Filler 43 / GRM	1.95	60	≥ 43	74 ± 5	Rubber		✓	✓	
Filler 55 / GRM	1.89	65	≥ 58	70 ± 5	Rubber		✓	✓	Ideal for CPR applications for B2ca and Cca class cables.
Filler 68 / GRM	1,88	68	65	48 ± 5	Rubber	✓		✓	Ideal for CPR applications for B2ca class cables.
Filler 71 ST / GRM	1.83	67	≥ 70	66 ± 5	Rubber	✓		✓	Ideal for CPR applications for B2ca class cables.
Filler 77 / GRM	1.83	67	≥ 70	66 ± 5	Rubber	✓		✓	Ideal for CPR applications for B2ca class cables.

Vibiplast	Specific Gravity	Hardness	Oxygen Index	Mooney Viscosity	Product base	Drummability of the product		Suitable for Tandem	Notes
<i>Product Name</i>	<i>kg/dm<sup>3</sup></i>	<i>Shore A</i>	<i>% O<sub>2</sub></i>	<i>ML (1+4) 100°C</i>		Drummable	Not Drummable		
HL Filler 100	1.72	Shore D 51	> 32	32	Polyolefin	✓		✓	
HL Filler 105	1.85	Shore D 55	41	70	Polyolefin	✓		✓	
HL Filler 110	1,68	Shore D 55	≥ 40	75	Polyolefin	✓		✓	Ideal for CPR applications for B2ca and Cca class cables.
HL RIEMPITIVO GUAINETTA	1.55	Shore D 52	≥ 32	---	Polyolefin	✓		✓	